

IRISECO®

pre-dispersed VOC-free, APEO-free, binder-free, water based organic and inorganic pigment pastes, compatible with aqueous paint preparations

IRIS GREEN s.r.l.
Via del Ferro 374/a
59100 Prato (PO) - Italy
Phone: +39.0574.540014
Fax: +39.0574.644282
Web: www.iris-green.com
E-mail: info@iris-green.com



IRISECO®

pre-dispersed VOC-free, APEO-free, binder-free, water based organic and inorganic pigment pastes, compatible with aqueous paint preparations

Full Shade (TP)	Tint Shade (TA)	IRISECO	Colour Index	Pigment Content %	Light Fastness		Weathering Fastness		Fastness	
					TP	TA	TP	TA	TP	TA
		GIALLO LUCE G	P.Y.53	60	8	7/8	5	5	5	5
		GIALLO BV	P.Y.184	60	8	7/8	5	4/5	5	3/4
		GIALLO BTR	P.Y.184	60	8	7/8	5	4/5	5	3/4
		GIALLO LUCE R	P.Br.24	65	8	7/8	5	5	5	5
		GIALLO 910	P.Y.42	60	8	7/8	5	5	5	5
		GIALLO ARANCIO	P.Y.42	50	8	7/8	5	5	5	5
		ARANCIO 20-H	MIX	50	8	7/8	5	5	5	5
		BRUNO 291	P.R.101	45	8	7/8	5	5	5	5
		ROSSO 10	P.R.101	65	8	7/8	5	5	5	5
		ROSSO 30 NUOVO	P.R.101	65	8	7/8	5	5	5	5
		BRUNO 61	MIX	65	8	7/8	5	5	5	5
		VERDE LUCE 5G	P.G.50	65	8	7/8	5	5	5	5
		VERDE G	P.G.17	72	8	7/8	5	5	5	5
		BLU LUCE G	P.B.36	55	8	7/8	5	5	5	5
		BLU LUCE R	P.B.28	60	8	7/8	5	5	5	5
		NERO 4T	P.B.11	55	8	7/8	5	5	5	5
		NERO 3 NUOVO	P.Bk.33	70	8	7/8	5	5	5	5
		BIANCO R	P.W.6	70	8	7/8	5	5	5	5

TP: 5% in full-shade emulsion paint TA: 1% in emulsion paint (20% TiO₂)

new range

PIGMENT PREPARATIONS

VOC free

The color sample are printed and therefore slight variations in shade are possible. The prints cannot be used for tests of pigment properties. This information is based on our present state of knowledge and is intended to provide general notes on our product and their uses and we don't undertake any responsibility.



IRIS GREEN

IRIS GREEN

pigment preparations
pigments
dyes
pearlescent pigments
metal powder and pastes

Full Shade (TP)	Tint Shade (TA)	IRISECO	Colour Index	Pigment Content %	Light Fastness		Weathering Fastness		Fastness	
					TP	TA	TP	TA	TP	TA
		GIALLO 10G	P.Y.3	45	6/7	6	4	3	4/5	4/5
		GIALLO HG	P.Y.154	35	8	7/8	5	4/5	5	5
		GIALLO 2GX-FR	P.Y.74	47	7	6/7	4	3	4/5	4/5
		GIALLO WGC	P.Y.97	31	6/7	6	4	3	5	5
		GIALLO HR	P.Y.83	40	6/7	6	3	2	4	4
		ARANCIO R	P.O.5	50	6/7	5/6	3/4	3	4	4
		ARANCIO HL	P.O.36	25	7	6/7	4	3	5	5
		SCARLATTO GG	P.R.168	40	8	7/8	5	4/5	5	5
		ROSSO BS	P.R.254	40	6/7	6	3/4	2/3	5	5
		ROSSO BB	P.R.112	50	6/7	5/6	3/4	2/3	3/4	4
		ROSSO EXTRA 410-H	P.V.19	30	7/8	7	4/5	4	5	5
		ROSA FB	P.R.122	35	7/8	7	4/5	4	5	5
		BORDEAUX FGR	P.R.14	35	6/7	6	3/4	2/3	5	5
		VIOLETTO BN CONC.	P.V.23	30	7/8	7	4/5	4	5	5
		BLU FFG	P.B.15.0	45	7/8	7	4/5	4	5	5
		BLU G	P.B.15.3	45	7/8	7	4/5	4	5	5
		VERDE G	P.G.7	50	7/8	7	4/5	4	5	5
		NERO N	P.Bk.7	40	7/8	7	4/5	4	5	5

TP: 5% in full-shade emulsion paint TA: 1% in emulsion paint (20% TiO₂)

new range

PIGMENT PREPARATIONS

VOC free

The color sample are printed and therefore slight variations in shade are possible. The prints cannot be used for tests of pigment properties. This information is based on our present state of knowledge and is intended to provide general notes on our product and their uses and we don't undertake any responsibility.

IRISWET®

pre-dispersed binder-free and solvent-free water based organic pigment pastes, compatible with aqueous paint preparation

Full Shade (TP)	Tint Shade (TA)	IRISWET	Colour Index	Pigment Content %	Light Fastness		Weathering Fastness		Fastness	
					TP	TA	TP	TA	TP	TA
		GIALLO 10G	P.Y.3	45	6/7	6	4	3	4/5	4/5
		GIALLO HG	P.Y.154	35	8	7/8	5	4/5	5	5
		GIALLO 2GX-FR	P.Y.74	47	7	6/7	4	3	4/5	4/5
		GIALLO G	P.Y.1	50	6/7	5/6	3/4	2/3	4/5	4/5
		GIALLO RP	P.Y.65	40	6/7	6	4	3	5	5
		GIALLO HR	P.Y.83	40	6/7	6	3	2	4	4
		ARANCIO AR	P.O.43	25	7	6/7	4	3/4	5	5
		ARANCIO R	P.O.5	50	6/7	5/6	3/4	3	4	4
		ARANCIO F5G	P.O.13	40	5	4	2/3	2	4	4
		SCARLATTO GG	P.R.168	40	6	7/8	5	4/5	5	5
		ROSSO BS	P.R.254	40	6/7	6	3/4	2/3	5	5
		ROSSO BB	P.R.112	50	6/7	5/6	3/4	2/3	3/4	4
		ROSSO EXTRA 410-H	P.V.19	30	7/8	7	4/5	4	5	5
		ROSA FB	P.R.122	35	7/8	7	4/5	4	5	5
		VIOLETTO BN CONC.	P.V.23	30	7/8	7	4/5	4	5	5
		BLU FFG	P.B.15.0	45	7/8	7	4/5	4	5	5
		BLU G	P.B.15.3	45	7/8	7	4/5	4	5	5
		VERDE G	P.G.7	50	7/8	7	4/5	4	5	5
		NERO N	P.Bk.7	40	7/8	7	4/5	4	5	5

TP: 5% in full-shade emulsion paint TA: 1% in emulsion paint (20% TiO₂)

PIGMENT PREPARATIONS

The color sample are printed and therefore slight variations in shade are possible. The prints cannot be used for tests of pigment properties. This information is based on our present state of knowledge and is intended to provide general notes on our product and their uses and we don't undertake any responsibility.

IRISOXOL®

pre-dispersed binder-free and solvent-free water based inorganic pigment pastes, compatible with aqueous paint preparation

Full Shade (TP)	Tint Shade (TA)	IRISOXOL	Colour Index	Pigment Content %	Light Fastness		Weathering Fastness		Fastness	
					TP	TA	TP	TA	TP	TA
		GIALLO LUCE G	P.Y.53	60	8	7/8	5	5	5	5
		GIALLO BV	P.Y.184	60	8	7/8	5	4/5	5	3/4
		GIALLO BTR	P.Y.184	60	8	7/8	5	4/5	5	3/4
		GIALLO LUCE R	P.Br.24	65	8	7/8	5	5	5	5
		GIALLO 910	P.Y.42	60	8	7/8	5	5	5	5
		GIALLO ARANCIO	P.Y.42	50	8	7/8	5	5	5	5
		ARANCIO 20-H	MIX	50	8	7/8	5	5	5	5
		BRUNO 291	P.R.101	45	8	7/8	5	5	5	5
		ROSSO 10	P.R.101	65	8	7/8	5	5	5	5
		ROSSO 30 NUOVO	P.R.101	65	8	7/8	5	5	5	5
		BRUNO 61	MIX	65	8	7/8	5	5	5	5
		VERDE LUCE 5G	P.G.50	65	8	7/8	5	5	5	5
		VERDE G	P.G.17	72	8	7/8	5	5	5	5
		BLU LUCE G	P.B.36	55	8	7/8	5	5	5	5
		BLU LUCE R	P.B.28	60	8	7/8	5	5	5	5
		ULTRAMARINO 13	P.B.29	60	8	7/8	5	5	1	2/3
		NERO 4T	P.Bk.11	55	8	7/8	5	5	5	5
		NERO 3 NUOVO	P.Bk.33	70	8	7/8	5	5	5	5
		BIANCO R	P.W.6	70	8	7/8	5	5	5	5

TP: 5% in full-shade emulsion paint TA: 1% in emulsion paint (20% TiO₂)

PIGMENT PREPARATIONS

The color sample are printed and therefore slight variations in shade are possible. The prints cannot be used for tests of pigment properties. This information is based on our present state of knowledge and is intended to provide general notes on our product and their uses and we don't undertake any responsibility.

IRISCOLOR®

pre-dispersed binder-free and solvent-free water based inorganic and organic pigment pastes, compatible with aqueous and non-aqueous solvent containing paint preparation

Full Shade (TP)	Tint Shade (TA)	IRISCOLOR	Colour Index	Pigment Content %	Light Fastness		Weathering Fastness		Fastness	
					TP	TA	TP	TA	TP	TA
		GIALLO LIMONE ER	P.Y.184	30	8	7/8	5	4/5	5	3/4
		GIALLO FREDDO	P.Y.3	30	6/7	6	4	3	4/5	4/5
		GIALLO CALDO ER	P.Y.154	25	8	7/8	5	4/5	5	5
		GIALLO BRILLANTE	P.Y.74	20	7	6/7	4	3	4/5	4/5
		GIALLO ORO	P.Y.83	20	6/7	6	3	2	4	4
		GIALLO OCRA OX-ER	P.Y.42	50	8	7/8	5	5	5	5
		ARANCIO BRILL OX-ER	P.R.101	48	8	7/8	5	5	5	5
		ROSSO FUOCO ER	P.R.168	20	8	7/8	5	4/5	5	5
		ROSSO VIVO	P.R.112	30	6/7	5/6	3/4	2/3	3/4	4
		ROSA	P.R.122	20	7/8	7	4/5	4	5	5
		VIOLETTO	P.V.23	15	7/8	7	4/5	4	5	5
		ROSSO OX-ER	P.R.101	50	8	7/8	5	5	5	5
		BRUNO OX-ER	MIX	60	8	7/8	5	5	5	5
		VERDE OX-ER	P.G.17	55	8	7/8	5	5	5	5
		VERDE	P.G.7	25	7/8	7	4/5	4	5	5
		BLU COBALTO OX-ER	P.B.28	45	8	7/8	5	5	5	5
		BLU	P.B.15.3	30	7/8	7	4/5	4	5	5
		NERO	P.Bk.7	15	7/8	7	4/5	4	5	5
		BIANCO OX-ER	P.W.6	50	8	7/8	5	5	5	5

TP: 5% in full-shade emulsion paint TA: 1% in emulsion paint (20% TiO₂)

PIGMENT PREPARATIONS

The color sample are printed and therefore slight variations in shade are possible. The prints cannot be used for tests of pigment properties. This information is based on our present state of knowledge and is intended to provide general notes on our product and their uses and we don't undertake any responsibility.

PIGMENTS

IRISPIGMENT® are pigments in powder for paints, printing inks and so on..

Colour Index	IRISPIGMENT	Colour Index	IRISPIGMENT
P.Y.1	YELLOW G	P.R.48.2	RUBINE BR
P.Y.3	YELLOW 10 GE	P.R.57.1	RUBINE WBI
P.Y.12	YELLOW TD	P.R.101	OXIDE RED 110
P.Y.13	YELLOW XR	P.R.101	OXIDE RED 130
P.Y.14	YELLOW TRS	P.R.146	CARMINE LY
P.Y.17	YELLOW 2G	P.R.170	RED F5QN
P.Y.42	OXIDE YELLOW 920	P.V.23	VIOLET B
P.Y.53	YELLOW G/M/MO	P.V.23	VIOLET R
P.Y.65	YELLOW RN	P.B.15.0	BLUE R
P.Y.74	YELLOW GW	P.B.15.1	BLUE RP
P.Y.74	YELLOW GXO	P.B.15.3	BLUE GP
P.Y.83	YELLOW HR	P.B.15.3	BLUE WBI
P.Y.97	YELLOW GP	P.B.15.4	BLUE KS
P.Br.24	YELLOW R/M/MO	P.B.28	BLUE R/M/MO
P.O.5	ORANGE GN	P.B.36	BLUE G/M/MO
P.O.13	ORANGE GS	P.G.7	GREEN Y
P.O.34	ORANGE TR	P.G.7	GREEN B
P.R.2	RED DTR	P.G.17	CHROME OXIDE GREEN
P.R.48.2	RUBINE SH	P.G.50	GREEN 5G/M/MO
P.R.48.2	RUBINE BW	P.Bk.11	OXIDE BLACK 318

DYES

Dyestuffs for wood stains, coatings, inks, leather industry and so on..

Colour Index	Metal-complex solvent dyes	Metal-complex Salt-free dyes	Dyes
S.Y.2	▲		
S.Y.82	▲		
S.R.8	▲		
S.R.122	▲		
S.Bk.27	▲		
A.R.414		▲	
A.Y.232		▲	
A.Br.282		▲	
A.Br.355		▲	
A.Y.25			▲
A.O.3			▲
A.B.25			▲
A.R.6			▲
A.Br.4			▲

METAL POWDER & PASTES

1. Bronze powders and pastes
2. Aluminium powders and flakes
3. Granulated aluminium
4. Aluminium paste
5. Copper and messing granulate

PEARLESCENT PIGMENTS

1. Silver series (anatase and rutile)
2. Golden series
3. Metallic series
4. Interference series
5. Polychrome series